



**HERCULUX**  
恒坤光电

Chengdu HercuLux Photoelectric  
Technology Co.,Ltd  
**Product Approval**

Approval number :

Customer :

Manufacturer : Chengdu HercuLux Photoelectric Technology Co.,Ltd

PN	Code	Product
HK-HG-68@32-15-D9-21-1g-1	1.08.02222	HK Gemini 68-32 -15 degree reflective cup
HK-HG-68@32-24-D12-21-1g-1	1.08.02241	HK Gemini 68-32 -24 degree reflective cup
HK-HG-68@32-36-D12-21-1g-1	1.08.02317	HK Gemini 68-32 -36 degree reflective cup
HK-HG-68@32-50-D12-21-1g-1	1.08.02331	HK Gemini 68-32 -50 degree reflective cup



Supplier confirmation				Client confirmation			
Proposed		DATE		Qualified <input type="checkbox"/>		DATE	
Project manager		DATE		Unqualified <input type="checkbox"/>		DATE	
Audit		DATE		Audit		DATE	
Approved		DATE		Approved		DATE	
Stamp		DATE		Stamp		DATE	

( Confirmation of acceptance by both parties must be signed and sealed )

Factory: Chengdu Shuangliu District, Iot industrial park 2 road HercuLux Photoelectric Park

Phone : 028-85887727 ( 801 ) 028-85887990 ( 801 )

Fax : 028-85887730

<http://www.herculux.cn/>

Sales Dept: Shenzhen Nanshan District Nanshan Cloud Valley Innovation Industrial Park Comprehensive Service Building, 501-505

TEL: 0755-2937 1541

FAX: 0755-2907 5140

\*Approval In duplicate , for both supplier and customer.



**HERCULUX**  
恒坤光电


# Product Approval


TEL: 0755-2937 1541

FAX: 0755-2907 5140

<http://www.herculux.cn/>

Date updated: 2021/12/20

Product Picture:	
PN:	HK-HG-68@32-15-D9-21-1g-1
Size(L*W*H/Φ*H):	Φ:68mm; H:32mm
Material:	PC half aluminum plating
Efficiency:	\
Temperature(Topr):	Material extreme temperature resistance : -40°C to +120°C long-term use temperature : -40°C to +90°C
FWHM:	15°、24°、36°、50°
Matched LES:	D12(Use D9 15 °)




**Technical remark:**

1. The 3D map is not indicated for rounded corners and draft angle.
2. The dimensional tolerances are not specified according to GB/T 14486 2008 MT5.
3. The surface has no flash, shrinkage, bubbles and other defects.

Optical design			HK Gemini 68-32 -15 degree reflective cup	HK-HG-68@32-15-D9-21-1g-1		
Structure design				1.08.02222		
Review				Number of drawing	qty	weight
Validation				Material: C half aluminum plating CDHK		

MT5 Tolerance table (mm)	Basic size	<3	3~10	24~65	65~140	140~250	250~450	>450
	olerance valu	±0.1	±0.15	±0.35	±0.50	±0.80	±1.2	±2.0




**Technical remark:**

1. The 3D map is not indicated for rounded corners and draft angle.
2. The dimensional tolerances are not specified according to GB/T 14486 2008 MT5.
3. The surface has no flash, shrinkage, bubbles and other defects.

Optical design			HK Gemini 68-32 -24 degree reflective cup	HK-HG-68@32-24-D12-21-1g-1		
structure design				1.08.02241		
Review				number of drawing	qty	weight
Validation			Material: C half aluminum platir	CDHK		

MT5 Tolerance table (mm)	Basic size	<3	3~10	24~65	65~140	140~250	250~450	>450	
	olerance valu	±0.1	±0.15	±0.35	±0.50	±0.80	±1.2	±2.0	




**Technical remark:**

1. The 3D map is not indicated for rounded corners and draft angle.
2. The dimensional tolerances are not specified according to GB/T 14486 2008 MT5.
3. The surface has no flash, shrinkage, bubbles and other defects.

Optical design			HK Gemini 68-32 -36 degree reflective cup	HK-HG-68@32-36-D12-21-1g-1		
structure design				1.08.02317		
Review				number of drawing	qty	weight
Validation				Material: C half aluminum platir CDHK		

MT5 Tolerance table (mm)	Basic size	<3	3~10	24~65	65~140	140~250	250~450	>450	
	olerance valu	±0.1	±0.15	±0.35	±0.50	±0.80	±1.2	±2.0	





**Technical remark:**

1. The 3D map is not indicated for rounded corners and draft angle.
2. The dimensional tolerances are not specified according to GB/T 14486 2008 MT5.
3. The surface has no flash, shrinkage, bubbles and other defects.

Optical design			HK Gemini 68-32 -50 degree reflective cup	HK-HG-68@32-50-D12-21-1g-1		
structure design				1.08.02331		
Review				number of drawing	qty	weight
Validation			Material: C half aluminum platir	CDHK		

MT5 Tolerance table (mm)	Basic size	<3	3~10	24~65	65~140	140~250	250~450	>450	
	olerance valu	±0.1	±0.15	±0.35	±0.50	±0.80	±1.2	±2.0	



Intensity data: (deg , cd) C0-180



A	I	A	I	A	I	A	I	A	I	A	I
-90.0	0.4293	-58.5	1.633	-27.0	70.02	4.5	2241	36.0	27.87	67.5	0.2515
-88.5	0.3271	-57.0	2.338	-25.5	83.45	6.0	1749	37.5	24.43	69.0	0.2689
-87.0	0.3261	-55.5	3.272	-24.0	100.4	7.5	1301	39.0	21.58	70.5	0.2918
-85.5	0.2925	-54.0	4.387	-22.5	121.8	9.0	934.5	40.5	19.01	72.0	0.3177
-84.0	0.2602	-52.5	5.636	-21.0	147.1	10.5	658.5	42.0	15.70	73.5	0.5151
-82.5	0.2181	-51.0	6.941	-19.5	176.5	12.0	471.3	43.5	13.78	75.0	0.3179
-81.0	0.2306	-49.5	8.371	-18.0	207.8	13.5	341.6	45.0	12.01	76.5	0.3069
-79.5	0.1576	-48.0	9.892	-16.5	250.1	15.0	265.9	46.5	10.39	78.0	0.2819
-78.0	0.2852	-46.5	11.60	-15.0	308.7	16.5	219.9	48.0	8.880	79.5	0.2509
-76.5	0.3261	-45.0	13.43	-13.5	399.3	18.0	184.5	49.5	7.407	81.0	0.2405
-75.0	0.3452	-43.5	15.38	-12.0	543.5	19.5	154.1	51.0	6.016	82.5	0.2336
-73.5	0.3418	-42.0	17.76	-10.5	768.9	21.0	128.2	52.5	4.705	84.0	0.2483
-72.0	0.3401	-40.5	20.96	-9.0	1080	22.5	106.5	54.0	3.525	85.5	0.2856
-70.5	0.3097	-39.0	23.53	-7.5	1479	24.0	88.92	55.5	2.515	87.0	0.3149
-69.0	0.2825	-37.5	26.67	-6.0	1949	25.5	74.68	57.0	1.753	88.5	0.3271
-67.5	0.2788	-36.0	30.17	-4.5	2431	27.0	63.47	58.5	1.175	90.0	0.2599
-66.0	0.2848	-34.5	34.22	-3.0	2855	28.5	54.34	60.0	0.6833		
-64.5	0.3082	-33.0	38.83	-1.5	3125	30.0	47.10	61.5	0.3440		
-63.0	0.3497	-31.5	44.07	0.0	3182	31.5	41.17	63.0	0.2116		
-61.5	0.5617	-30.0	50.83	1.5	3050	33.0	36.47	64.5	0.2628		
-60.0	1.045	-28.5	59.35	3.0	2708	34.5	31.94	66.0	0.2570		

**Electricity Parameter:**

Current I: 0.1000A      Power: 3.259W  
 Voltage V: 32.59V      PF: 1.000

**Optical Parameter (Distance=2.410m):**

Equivalent Luminous flux:  $\Phi$  eff= 324.6lm      Efficiency: Eff=99.61lm/W  
 Diffuse angle: @ (25%): 19.9deg @ (50%): 13.6deg @ (75%): 8.6deg @ (50%): 13.6deg  
 Diffuse angle: @ (25%): 19.9deg @ (50%): 13.6deg @ (75%): 8.6deg @ (50%): 13.6deg  
 Imax=3182cd (C=0.0deg,G=0.0deg)      C0-180Plane Imax= 3182cd(G=0.0deg)  
    C0-180Plane I0= 3182cd



Intensity data:(deg , cd) C0-180

A	I	A	I	A	I	A	I	A	I	A	I
-90.0	0.2938	-58.5	1.177	-27.0	88.81	4.5	1497	36.0	26.78	67.5	0.3241
-88.5	0.3273	-57.0	1.732	-25.5	103.0	6.0	1365	37.5	22.74	69.0	0.3031
-87.0	0.3474	-55.5	2.712	-24.0	119.5	7.5	1196	39.0	19.59	70.5	0.2775
-85.5	0.3364	-54.0	3.349	-22.5	139.6	9.0	1011	40.5	16.74	72.0	0.2684
-84.0	0.3133	-52.5	4.420	-21.0	166.2	10.5	823.8	42.0	14.34	73.5	0.2804
-82.5	0.2816	-51.0	5.577	-19.5	205.0	12.0	651.5	43.5	12.21	75.0	0.2933
-81.0	0.2506	-49.5	6.800	-18.0	263.1	13.5	501.8	45.0	10.31	76.5	0.5202
-79.5	0.2307	-48.0	8.227	-16.5	354.7	15.0	375.0	46.5	8.613	78.0	0.3265
-78.0	0.2427	-46.5	9.892	-15.0	475.7	16.5	274.2	48.0	7.123	79.5	0.3271
-76.5	0.2964	-45.0	11.74	-13.5	621.3	18.0	211.9	49.5	5.805	81.0	0.3018
-75.0	0.2972	-43.5	13.78	-12.0	789.1	19.5	171.6	51.0	4.596	82.5	0.2690
-73.5	0.3380	-42.0	16.15	-10.5	969.9	21.0	145.1	52.5	3.504	84.0	0.2488
-72.0	0.3657	-40.5	18.97	-9.0	1157	22.5	124.7	54.0	2.558	85.5	0.2269
-70.5	0.3527	-39.0	22.17	-7.5	1323	24.0	107.6	55.5	1.785	87.0	0.2347
-69.0	0.3508	-37.5	26.14	-6.0	1462	25.5	91.91	57.0	1.217	88.5	0.2599
-67.5	0.3439	-36.0	30.91	-4.5	1560	27.0	78.14	58.5	0.8760	90.0	0.1240
-66.0	0.2296	-34.5	36.94	-3.0	1626	28.5	65.93	60.0	0.6073		
-64.5	0.3039	-33.0	44.38	-1.5	1661	30.0	54.88	61.5	0.4329		
-63.0	0.3316	-31.5	53.44	0.0	1668	31.5	45.50	63.0	0.4248		
-61.5	0.4874	-30.0	64.60	1.5	1642	33.0	37.78	64.5	0.4016		
-60.0	0.7825	-28.5	76.10	3.0	1588	34.5	31.58	66.0	0.3046		



**Electricity Parameter:**

Current I: 0.1000A      Power: 3.250W  
Voltage V: 32.50V      PF: 1.000

**Optical Parameter(Distance=2.410m):**

Equivalent Luminous flux:  $\Phi_{\text{eff}}=328.5\text{lm}$       Efficiency:  $\text{Eff}=101.10\text{lm/W}$   
Diffuse angle:       $\theta(25\%): 30.0\text{deg}$   $\theta(50\%): 22.0\text{deg}$   $\theta(75\%): 15.1\text{deg}$   $\theta(50\%): 22.0\text{deg}$   
Diffuse angle:       $\theta(25\%): 30.0\text{deg}$   $\theta(50\%): 22.0\text{deg}$   $\theta(75\%): 15.1\text{deg}$   $\theta(50\%): 22.0\text{deg}$   
Imax=1669cd (C=0.0deg,G=-0.5deg)      C0-180Plane Imax= 1669cd(G=-0.5deg)  
C0-180Plane I0= 1668cd





Intensity data:(deg , cd) C0-180

A	I	A	I	A	I	A	I	A	I	A	I
-90.0	0.2599	-58.5	1.401	-27.0	100.0	4.5	892.7	36.0	17.47	67.5	0.3699
-88.5	0.2942	-57.0	2.074	-25.5	141.1	6.0	866.7	37.5	15.71	69.0	0.3861
-87.0	0.3383	-55.5	2.876	-24.0	189.2	7.5	831.5	39.0	14.09	70.5	0.3937
-85.5	0.3700	-54.0	3.681	-22.5	249.4	9.0	787.5	40.5	12.02	72.0	0.3898
-84.0	0.3575	-52.5	4.390	-21.0	318.2	10.5	735.0	42.0	10.53	73.5	0.3410
-82.5	0.3238	-51.0	5.128	-19.5	391.2	12.0	676.1	43.5	9.207	75.0	0.3676
-81.0	0.2809	-49.5	5.946	-18.0	465.6	13.5	609.4	45.0	7.990	76.5	0.2804
-79.5	0.2622	-48.0	6.888	-16.5	539.9	15.0	538.9	46.5	6.819	78.0	0.2438
-78.0	0.2447	-46.5	8.128	-15.0	611.3	16.5	465.5	48.0	5.838	79.5	0.2458
-76.5	0.2593	-45.0	9.376	-13.5	678.6	18.0	389.2	49.5	4.985	81.0	0.2679
-75.0	0.3127	-43.5	10.71	-12.0	737.9	19.5	306.5	51.0	4.150	82.5	0.3108
-73.5	0.3644	-42.0	12.61	-10.5	789.7	21.0	239.0	52.5	3.394	84.0	0.3231
-72.0	0.4140	-40.5	14.28	-9.0	832.4	22.5	179.2	54.0	2.749	85.5	0.3593
-70.5	0.4511	-39.0	15.77	-7.5	866.6	24.0	130.3	55.5	1.809	87.0	0.3426
-69.0	0.4531	-37.5	17.66	-6.0	892.5	25.5	91.67	57.0	1.207	88.5	0.2884
-67.5	0.4430	-36.0	20.22	-4.5	909.9	27.0	65.32	58.5	0.8253	90.0	0.4839
-66.0	0.4393	-34.5	23.74	-3.0	919.7	28.5	47.64	60.0	0.5986		
-64.5	0.4508	-33.0	29.06	-1.5	924.3	30.0	35.00	61.5	0.4561		
-63.0	0.5057	-31.5	37.49	0.0	924.9	31.5	27.45	63.0	0.3932		
-61.5	0.6489	-30.0	50.57	1.5	921.2	33.0	22.81	64.5	0.3641		
-60.0	0.9232	-28.5	70.55	3.0	911.0	34.5	19.72	66.0	0.3640		

### Electricity Parameter:

Current I: 0.1000A      Power: 3.250W  
 Voltage V: 32.50V      PF: 1.000

### Optical Parameter(Distance=2.410m):

Equivalent Luminous flux:  $\Phi_{eff}=324.7lm$       Efficiency:  $Eff=99.91lm/W$

Diffuse angle:      @ (25%): 44.0deg @ (50%): 34.5deg @ (75%): 24.6deg @ (50%): 34.5deg

Diffuse angle:      @ (25%): 44.0deg @ (50%): 34.5deg @ (75%): 24.6deg @ (50%): 34.5deg

$I_{max}=925.0cd$  (C=0.0deg,G=-1.0deg)


C0-180Plane  $I_{max}=925.0cd$ (G=-1.0deg)

C0-180Plane  $I_0=924.9cd$



	Standard size	Upper Size limit	Lower size limit	Test result1	Test result2	Test result3	Test result4	Judgment	Remarks
1.Size	highly	31.8		32.12	32.09	32.06	32.17		
	The diameter of	68		67.9	67.82	67.88	67.86		Test environment: In 20 °C -25 °C environment to achieve thermal equilibrium after the test.
	The thickness of the	2.5		2.65	2.69	2.68	2.72		
	Gate shear can not affect the appearance of the lamp								
See attachment "Appearance Inspection Standards"									
2.Appearance Quality	See attachment "Appearance Inspection Standards"	E	No burr	No burr	No burr	No burr	OK		
			No stains	No stains	No stains	No stains			
3.Material	PC half aluminum plating			Color	Transparent			OK	
4.Optical index	Testing LED	D12(Use D9 15 °)							
	The recommended size and power rating of the LED light source recommended for this lens should be comparable to the source of the test, if it is required to be out of range. According to the heat dissipation capability of the lamp and the actual conditions of the use environment, the lens should be fully tested and tested to prevent the lens life.								
	FWHM	See light distribution curve							
	angle		13.6°	13.1°	13.2°	13.0°			
	K-value		9.8	10.3	10.12	10.39			
	Efficiency		74.70%	74.86%	73.85%	72.17%			
Facula	See the signature sample								
Comprehensive judgment	Qualified								

Remarks:  
 1、 Tool Number: V-Vernier Caliper 2D-Quadratic H-Height Gauge M-Tool Microscope P-Needle T-Thick Gauge R-Radius Gauge E-Visual.  
 2、 Ambient temperature on the size of the product refer to the table on the right



- Please wear clean gloves during the lens assembly process to prevent the lens surface from being contaminated.
- Try to avoid touching the total reflection surface when taking the lens.
- The lens surface is contaminated. Only use a soft cotton cloth dipped in analytically pure neutral solvent to wipe gently. Do not wipe with industrial solvents (alcohol, isopropanol, acetone, ether, toluene, xylene, carbon tetrachloride, MMA Body, etc.).
- The working temperature of the lens should be within the temperature resistance limit of the lens material. Exceeding the temperature resistance limit will cause the lens to crack or melt and affect the service life of the lens. It is recommended that the upper surface temperature of the LED colloid should be less than 120 degrees.

		Standard size	Upper Size limit	Lower size limit	Test result1	Test result2	Test result3	Test result4	Judgment	Remarks
1.Size	highly	31.8	/	/	31.92	31.93	31.96	31.93	/	
	The diameter of	68	/	/	67.83	67.85	67.84	67.83	/	Test environment: In 20 °C -25 °C environment to achieve thermal equilibrium after the test.
	The thickness of the	2.5	/	/	2.6	2.68	2.52	2.58	/	
Gate shear can not affect the appearance of the lamp										
See attachment "Appearance Inspection Standards"										

2.Appearance Quality	See attachment "Appearance Inspection Standards"	E	No burr	No burr	No burr	No burr	OK
			No stains	No stains	No stains	No stains	


3.Material	PC half aluminum plating	Color	Transparent	OK
------------	--------------------------	-------	-------------	----

4.Optical index	Testing LED	D12(Use D9 15 °)				
	The recommended size and power rating of the LED light source recommended for this lens should be comparable to the source of the test, if it is required to be out of range. According to the heat dissipation capability of the lamp and the actual conditions of the use environment, the lens should be fully tested and tested to prevent the lens life.					
	FWHM	See light distribution curve				
	angle	/	22.0°	21.9°	22.0°	21.7°
	K-value	/	5.08	5.05	5	5.16
	Efficiency	/	73.87%	74.00%	74.04%	74.07%
Facula	See the signature sample					

Comprehensive judgment	Qualified
------------------------	-----------


50mm :  
100mm : Number: V-Vernier  
150mm : D-Quadratic H-  
200mm : auge M-Tool  
250mm : pe P-Needle T-  
300mm : uge R-Radius  
-Visual.  
ent temperature on  
of the product refer  
le on the right


**PC product size changes with temperature table**




Temperature (°C)	50mm	100mm	150mm	200mm	250mm	300mm
0	0.00	0.00	0.00	0.00	0.00	0.00
10	0.05	0.10	0.15	0.20	0.25	0.30
20	0.10	0.20	0.30	0.40	0.50	0.60
30	0.15	0.30	0.45	0.60	0.75	0.90
40	0.20	0.40	0.60	0.80	1.00	1.20

1. Please wear clean gloves during the lens assembly process to prevent the lens surface from being contaminated.
2. Try to avoid touching the total reflection surface when taking the lens.
3. The lens surface is contaminated. Only use a soft cotton cloth dipped in analytically pure neutral solvent to wipe gently. Do not wipe with industrial solvents (alcohol, isopropanol, acetone, ether, toluene, xylene, carbon tetrachloride, MMA Body, etc.).
4. The working temperature of the lens should be within the temperature resistance limit of the lens material. Exceeding the temperature resistance limit will cause the lens to crack or melt and affect the service life of the lens. It is recommended that the upper surface temperature of the LED colloid should be less than 120 degrees.

		Standard size	Upper Size limit	Lower size limit	Test result1	Test result2	Test result3	Test result4	Judgment	Remarks																																										
1.Size	highly	31.8			31.96	31.96	32.01	32.05																																												
	The diameter of	68			67.87	67.85	67.82	67.82		Test environment: In 20 °C -25 °C environment to achieve thermal equilibrium after the test.																																										
	The thickness of the	2.5			2.58	2.6	2.68	2.6																																												
	Gate shear can not affect the appearance of the lamp																																																			
See attachment "Appearance Inspection Standards"																																																				
2.Appearance Quality	See attachment "Appearance Inspection Standards"	E	No burr	No burr	No burr	No burr			OK																																											
			No stains	No stains	No stains	No stains																																														
3.Material	PC half aluminum plating			Color	Transparent			OK																																												
4.Optical index	Testing LED	D12(Use D9 15 °)																																																		
	The recommended size and power rating of the LED light source recommended for this lens should be comparable to the source of the test, if it is required to be out of range. According to the heat dissipation capability of the lamp and the actual conditions of the use environment, the lens should be fully tested and tested to prevent the lens life.																																																			
	FWHM	See light distribution curve																																																		
	angle				34.5°	35°	35.5°	35.8																																												
	K-value				2.84	2.8	2.73	2.69																																												
	Efficiency				73.03%	73.45%	73.09%	73.14%																																												
Facula	See the signature sample																																																			
Comprehensive judgment	Qualified																																																			
Remarks:	<p>1、 Tool Number: V-Vernier Caliper 2D-Quadratic H-Height Gauge M-Tool Microscope P-Needle T-Thick Gauge R-Radius Gauge E-Visual.</p> <p>2、 Ambient temperature on the size of the product refer to the table on the right</p>																																																			
	<p style="text-align: center;"><b>PC product size changes with temperature table</b></p>  <table border="1"> <caption>Data for PC product size changes with temperature table</caption> <thead> <tr> <th>Temperature (°C)</th> <th>50mm</th> <th>100mm</th> <th>150mm</th> <th>200mm</th> <th>250mm</th> <th>300mm</th> </tr> </thead> <tbody> <tr> <td>0</td> <td>0.00</td> <td>0.00</td> <td>0.00</td> <td>0.00</td> <td>0.00</td> <td>0.00</td> </tr> <tr> <td>10</td> <td>0.02</td> <td>0.04</td> <td>0.06</td> <td>0.08</td> <td>0.10</td> <td>0.12</td> </tr> <tr> <td>20</td> <td>0.04</td> <td>0.08</td> <td>0.12</td> <td>0.16</td> <td>0.20</td> <td>0.24</td> </tr> <tr> <td>30</td> <td>0.06</td> <td>0.12</td> <td>0.18</td> <td>0.24</td> <td>0.30</td> <td>0.36</td> </tr> <tr> <td>40</td> <td>0.08</td> <td>0.16</td> <td>0.24</td> <td>0.32</td> <td>0.40</td> <td>0.48</td> </tr> </tbody> </table>										Temperature (°C)	50mm	100mm	150mm	200mm	250mm	300mm	0	0.00	0.00	0.00	0.00	0.00	0.00	10	0.02	0.04	0.06	0.08	0.10	0.12	20	0.04	0.08	0.12	0.16	0.20	0.24	30	0.06	0.12	0.18	0.24	0.30	0.36	40	0.08	0.16	0.24	0.32	0.40	0.48
Temperature (°C)	50mm	100mm	150mm	200mm	250mm	300mm																																														
0	0.00	0.00	0.00	0.00	0.00	0.00																																														
10	0.02	0.04	0.06	0.08	0.10	0.12																																														
20	0.04	0.08	0.12	0.16	0.20	0.24																																														
30	0.06	0.12	0.18	0.24	0.30	0.36																																														
40	0.08	0.16	0.24	0.32	0.40	0.48																																														
<p>1. Please wear clean gloves during the lens assembly process to prevent the lens surface from being contaminated.</p> <p>2. Try to avoid touching the total reflection surface when taking the lens.</p> <p>3. The lens surface is contaminated. Only use a soft cotton cloth dipped in analytically pure neutral solvent to wipe gently. Do not wipe with industrial solvents (alcohol, isopropanol, acetone, ether, toluene, xylene, carbon tetrachloride, MMA Body, etc.).</p> <p>4. The working temperature of the lens should be within the temperature resistance limit of the lens material. Exceeding the temperature resistance limit will cause the lens to crack or melt and affect the service life of the lens. It is recommended that the upper surface temperature of the LED colloid should be less than 120 degrees.</p>																																																				




	Standard size	Upper Size limit	Lower size limit	Test result1	Test result2	Test result3	Test result4	Judgment	Remarks																																										
1.Size	highly	31.8		31.91	31.86	31.96	31.92																																												
	The diameter of	68		67.84	67.87	67.83	67.87		Test environment: In 20 °C -25 °C environment to achieve thermal equilibrium after the test.																																										
	The thickness of the	2.5		2.6	2.53	2.5	2.52																																												
	Gate shear can not affect the appearance of the lamp																																																		
See attachment "Appearance Inspection Standards"																																																			
2.Appearance Quality	See attachment "Appearance Inspection Standards"	E	No burr	No burr	No burr	No burr	OK																																												
			No stains	No stains	No stains	No stains																																													
3.Material	PC half aluminum plating			Color	Transparent		OK																																												
4.Optical index	Testing LED	D12(Use D9 15 °)																																																	
	The recommended size and power rating of the LED light source recommended for this lens should be comparable to the source of the test, if it is required to be out of range. According to the heat dissipation capability of the lamp and the actual conditions of the use environment, the lens should be fully tested and tested to prevent the lens life.																																																		
	FWHM	See light distribution curve																																																	
	angle		51.1°	51.3°	51.0°	51.2°																																													
	K-value																																																		
	Efficiency		72.86%	73.10%	73.35%	73.05%																																													
Facula	See the signature sample																																																		
Comprehensive judgment	Qualified																																																		
Remarks:	<p>1、 Tool Number: V-Vernier Caliper 2D-Quadratic H-Height Gauge M-Tool Microscope P-Needle T-Thick Gauge R-Radius Gauge E-Visual.</p> <p>2、 Ambient temperature on the size of the product refer to the table on the right</p>																																																		
	<p style="text-align: center;"><b>PC product size changes with temperature table</b></p>  <table border="1"> <caption>Data extracted from the graph: Length changes (mm) vs Temperature (°C)</caption> <thead> <tr> <th>Temperature (°C)</th> <th>50mm</th> <th>100mm</th> <th>150mm</th> <th>200mm</th> <th>250mm</th> <th>300mm</th> </tr> </thead> <tbody> <tr> <td>0</td> <td>0.00</td> <td>0.00</td> <td>0.00</td> <td>0.00</td> <td>0.00</td> <td>0.00</td> </tr> <tr> <td>10</td> <td>0.05</td> <td>0.10</td> <td>0.15</td> <td>0.20</td> <td>0.25</td> <td>0.30</td> </tr> <tr> <td>20</td> <td>0.10</td> <td>0.20</td> <td>0.30</td> <td>0.40</td> <td>0.50</td> <td>0.60</td> </tr> <tr> <td>30</td> <td>0.15</td> <td>0.30</td> <td>0.45</td> <td>0.60</td> <td>0.75</td> <td>0.90</td> </tr> <tr> <td>40</td> <td>0.20</td> <td>0.40</td> <td>0.60</td> <td>0.80</td> <td>1.00</td> <td>1.20</td> </tr> </tbody> </table>									Temperature (°C)	50mm	100mm	150mm	200mm	250mm	300mm	0	0.00	0.00	0.00	0.00	0.00	0.00	10	0.05	0.10	0.15	0.20	0.25	0.30	20	0.10	0.20	0.30	0.40	0.50	0.60	30	0.15	0.30	0.45	0.60	0.75	0.90	40	0.20	0.40	0.60	0.80	1.00	1.20
Temperature (°C)	50mm	100mm	150mm	200mm	250mm	300mm																																													
0	0.00	0.00	0.00	0.00	0.00	0.00																																													
10	0.05	0.10	0.15	0.20	0.25	0.30																																													
20	0.10	0.20	0.30	0.40	0.50	0.60																																													
30	0.15	0.30	0.45	0.60	0.75	0.90																																													
40	0.20	0.40	0.60	0.80	1.00	1.20																																													
<p>1. Please wear clean gloves during the lens assembly process to prevent the lens surface from being contaminated.</p> <p>2. Try to avoid touching the total reflection surface when taking the lens.</p> <p>3. The lens surface is contaminated. Only use a soft cotton cloth dipped in analytically pure neutral solvent to wipe gently. Do not wipe with industrial solvents (alcohol, isopropanol, acetone, ether, toluene, xylene, carbon tetrachloride, MMA Body, etc.).</p> <p>4. The working temperature of the lens should be within the temperature resistance limit of the lens material. Exceeding the temperature resistance limit will cause the lens to crack or melt and affect the service life of the lens. It is recommended that the upper surface temperature of the LED colloid should be less than 120 degrees.</p>																																																			

PN	HK-HG-68@32-15-D9-21-1g-1		Product Name	HK Gemini 68-32 -15 degree reflective cup			
Product material	PC half aluminum plating		Customer				
Package diagram	 <p style="text-align: center;"> <span>Single</span>      <span>Vacuum package</span>      <span>Box package</span> </p>						
Product packing	8	A/ Box	4	pcs/Layer			
	4	Layer/Box	128	A/ Carton			
Packaging Materials	NO.	Part No	Part name	Size	Dosage	Unit	Remarks
	1	2. 07. 0080	Blister box	23cm*21cm	16	BAG	
	2	2. 08. 0001	PE film	25cm*27cm	16	PCS	
	3	2. 06. 0005	Reel label paper	62mm*42mm	16	PCS	
	4	2. 06. 0005	Box label paper	62mm*70mm	1	PCS	
	5	2. 06. 0003	big plate	46cm*42cm	5	PCS	
	6	2. 06. 0018	big flat carton	48cm*44cm*19cm	1	PCS	
Remarks	Scattered packaging is not restricted by this specification, the customer has the requirements of the customer shall prevail						

Special notice

When glue pass through holes, columns and other structures, or part of the thin structure, will form a weld line. The product which uses multi-point injection welding line will appear because of the combination of sol, as shown below:

Syntner



Please note :

The appearance of lines in the structure of the product as well as at the screw hole is a normal phenomenon, will not affect the actual use of the product, and can not be avoided at this stage.



## Appearance inspection standards

## 1 Operating procedures

## 1.1 Sampling standards, sampling plan and AQL

Test level : GB/T2828.1-2012 The first part is according to the acceptance quality limit (AQL) retrieval batch inspection sampling plan, general inspection level II level, CR class defect coefficient 0, MA defect rejection level AQL = 0.65, MI class defect rejection level AQL = 1.0; defect level please see 5.4.

## 2 Code table

Code	Code description	Unit	Code	Code description	Unit
N	Amount/pcs	pcs	D	Diameter	mm
L	Length	mm	H	Depth	mm
W	Width	mm	DS	Distance	mm
S	Proportion	mm <sup>2</sup>	SS	Offset	mm

## 3 Test conditions

3.1 Sight distance and working hours: Sight distance should be 30-35cm, each side of the inspection time does not exceed 12s, the visual angle of 45-135 degrees;

3.2 Light: 2x40w cool white fluorescent lamp, the light source is 500-550mm away from the lens surface; in order to make the appearance defect can be correctly recognized, the illumination should be 500-1000Lux, and the observation time is 10 seconds.

3.3 Visual inspection staff should be 1.0 (including corrected visual acuity) above, no color blindness, color weakness.

## 4 Appearance inspection standards

Test items	Judging standard	Inspection equipment	Defect level		
		Testing method	MI	MA	CR
Check the sample	When start the machine and process, all products have to check the appearance of the sample, the appearance of the sample is divided into qualified samples and limited samples.	Sample comparison, visual			√
	1: Qualified sample refers to the appearance and structure standard of the product which recognized by the client, the sample size should be confirmed before mass production;				
	2: The limited sample refers to the limit of a particular exceptionally developed sample. Limit the sample only for its specific point of exception to confirm; The priority is higher than the other criteria in this table. When there is a limited sample, the limit sample shall prevail.				
Raw edge	Not allowed to affect the size and assembly	Visual, point card		√	

Scratch	1: Non-optical surface and non-exposed surface scratches should be visually insignificant and the length is less than 1/10 of the maximum surface size.	Visual, point card, calipers		√	
Fingerprint	Fingerprints are not allowed on all products	Visual		√	
Foreign objects, black spots, white spots	The product may not be attached to foreign objects, including oil, fiber, dregs of water gap and so on				√
Deformation	Insufficient filling shall not affect the appearance of the assembly and the exposed surfaces.	Visual, feeler			√
Poor ejection	Products may not appear bad ejection, including no convex top, thimble printed on the assembly surface shall not be higher than the product surface, non-assembled surface thimble height should not exceed the product size tolerances; thimble printing should be less than the product surface and no more than 0.3; thimble surface treatment should be consistent with the product side.	Visual, point card		√	
	Ejection strain: the optical surface and the appearance of the exposed surface after assembly are not allowed to have a strain, and the structural surface does not allow visual obvious strain.				
Insufficient filling	Insufficient filling shall not affect the appearance of the assembly and the exposed surfaces , The signature sample shall prevail.	Visual, point card		√	
Shrink	When the entire surface of the product shrinks, the optical properties and dimensions must meet the requirements, and the visual will not significantly affect the appearance.Part shrink reference point defects	Visual, point card		√	
Flow marks、Welding line	1 : Product does not allow the presence of flow marks and welding lines unless the structure can not be avoided;	Visual		√	
	2: The remaining flow marks shall not appear in the optical surface, a single L ≤ 10mm, no more than two				
Bubble	No bubbles are allowed	Visual		√	
Foreign objects, black spots, white spots	Not obvious or D ≤ 0.3mm black spots and foreign bodies in the area of 100x100mm not more than 1; Exceeded foreign matter black spots is judged bad.	Visual, point card	√		
Damaged	No damage is allowed	Visual			√
Cold glue	Optical surface may not have cold glue, non-optical surface cold glue should meet the visual is not obvious.	Visual	√		
Bad incision	1: Do not affect the product size, shall not penetrate the optical surface, the cut should be smooth;	Visual			√
	2: Laser cutting products, the optical surface burns shall not occur after the processing is completed. Beading must not affect product installation				
	3: Three molds and hot runner gate shall not appear residue.				
Scrub	Scrub surface should be uniform, off the scrub phenomenon should not be obvious , A single off scrub imprint requires D ≤ 1 mm and no more than 1 area within a 50x50 mm area	Visual		√	